

# Window Film Specification Sheet

Product	VLT	Visible light reflectance	Shading Coefficient (SC)	Solar Absorption	Total Solar Energy Rejected	UV Rejection	IRR (1025 nm)	Glare Reduction	Adhesive Type	Thickness	Liner Orientation
Black 05	5%	6%	0.66	50%	43%	>99%	13%	94%	PSA	1.5 Mil	Out
Black 15	15%	6%	0.68	49%	42%	>99%	13%	83%	PSA	1.5 Mil	Out
Black 20	19%	6%	0.69	45%	39%	>99%	13%	79%	PSA	1.5 Mil	Out
Black 30	31%	6%	0.74	42%	36%	>99%	13%	66%	PSA	1.5 Mil	Out
Black 36	36%	6%	0.73	42%	35%	>99%	13%	63%	PSA	1.5 Mil	Out
Black 40	42%	6%	0.77	39%	34%	>99%	13%	54%	PSA	1.5 Mil	Out
Black 50	49%	6%	0.80	32%	30%	>99%	13%	46%	PSA	1.5 Mil	Out
Black 56	56%	6%	0.80	31%	29%	>99%	13%	41%	PSA	1.5 Mil	Out
Black Ceramic 05	5%	8%	0.40	82%	63%	>99%	60%	95%	PSA	1.5 Mil	Out
Black Ceramic 15	16%	8%	0.41	80%	59%	>99%	60%	82%	PSA	1.5 Mil	Out
Black Ceramic 20	21%	8%	0.42	78%	56%	>99%	60%	79%	PSA	1.5 Mil	Out
Black Ceramic 30	31%	8%	0.47	71%	55%	>99%	60%	68%	PSA	1.5 Mil	Out
Black Ceramic 40	40%	8%	0.49	69%	53%	>99%	60%	60%	PSA	1.5 Mil	Out
Black Ceramic 50	47%	8%	0.54	64%	50%	>99%	60%	50%	PSA	1.5 Mil	Out
Black Ceramic 56	54%	8%	0.58	57%	49%	>99%	60%	42%	PSA	1.5 Mil	Out
Ceramic i3 05	5%	6%	0.34	89%	71%	>99%	93%	95%	PSA	1.5 Mil	Out
Ceramic i3 15	15%	7%	0.35	87%	68%	>99%	93%	89%	PSA	1.5 Mil	Out
Ceramic i3 22	22%	7%	0.38	83%	66%	>99%	93%	79%	PSA	1.5 Mil	Out
Ceramic i3 33	33%	7%	0.46	73%	62%	>99%	93%	59%	PSA	1.5 Mil	Out
Ceramic i3 40	40%	8%	0.47	70%	60%	>99%	93%	50%	PSA	1.5 Mil	Out
Ceramic i3 56	56%	8%	0.55	65%	56%	>99%	93%	38%	PSA	1.5 Mil	Out
Ceramic i3 70	67%	7%	0.59	57%	50%	>99%	93%	27%	PSA	2.0 Mil	Out
Air Ceramic 70	70%	7%	0.60	54%	50%	>99%	89%	25%	PSA	2.0 Mil	Out
Air Ceramic 80	78%	9%	0.66	46%	44%	>99%	68%	15%	PSA	2.0 Mil	Out